



# TEST REPORT

## DC2893/7

### TESTING OF WPM 1000RR MEMBRANE TO THE REQUIREMENTS OF AS4654.1 2012

#### CLIENT

Ardex New Zealand Limited  
32 Lane Street  
Woolston  
Christchurch

PROJECT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**1 of 9**

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

# TEST SUMMARY

## Objective

Testing was completed of WPM 1000RR membrane to the requirements of AS4654.1 2012 *Waterproofing membranes for external above-ground use Part 1: Materials*.

## Test sponsor

Ardex New Zealand Limited  
32 Lane Street  
Woolston  
Christchurch

## Description of test specimen

The client supplied sheet membrane samples to be tested.

## LIMITATION

The results reported here relate only to the items tested.

## TERMS AND CONDITIONS

This report is issued in accordance with the Terms and Conditions as detailed and agreed in the BRANZ Services Agreement for this work.



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**


PAGE:

**2 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

## SIGNATORIES



**Author**

Nigel Kell  
Senior Technician



**Reviewer**

Nick Marston  
Materials Team Leader

## DOCUMENT REVISION STATUS

ISSUE NO.	DATE ISSUED	DESCRIPTION
1	21 August 2017	Initial Issue



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**3 of 9**

THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT. EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

# 1. SUMMARY

## AS4654.1 Table 2.1 Requirements – Fully Bonded Membranes – WPM 1000RR Membrane

Note : #Results from testing WPM 750 membrane

PROPERTY REQUIRED	METHOD	RESULTS
Abrasion resistance	AS1580.403.2	N/A as non-exposed
#Bond strength	ASTM C794	Concrete 29 N Plywood 7 N
#Cyclic movement	CSIRO Moving Joint Test	Pass
Dimensional stability	ASTM D6207	Maximum length change = 3 mm
#Elongation at break	AS4654.1 Appendix A	>4.07 MPa >500 % Elongation - Class III
Field seam strength	N/A	N/A - achieved by the overlap and the method of adhesion
#Heat ageing	AS/NZS4858	>4.11 MPa >450 % Elongation
#Temperature resistance	AS4654.1 Clause 2.6	Pass
Ultraviolet resistance	AS4654.1 Table A4	N/A as non-exposed
#Tensile strength	AS4654.1 Table A4	>4.07 MPa >500 % Elongation
Thickness	Various methods	1.47mm (mean of sample supplied)
Durability	AS4654.1 Table A4	See Note 1
#Water vapour transmission rate	ASTM E96	0.23 g/m <sup>2</sup> /24 hours

### Notes:

1. Durability of membranes is a combined group of assessments as detailed in AS4654.1 Appendix A, Table A4.

#Control >4.07 MPa >500% Elongation

#Water immersion >3.99 MPa >500% Elongation

#Detergent immersion >3.90 MPa >500% Elongation

#Heat ageing >4.11 MPa >450% Elongation

Ultra violet N/A

Bioresistance Manufacturing guidelines for bioresistance to be followed



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**4 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

## 2. BOND STRENGTH

### 2.1 Testing

Testing carried out in accordance with ASTM C794.

### 2.2 Results

Results are an average of 4 samples.

Note : Results from testing WPM 750 membrane

Substrate	Average peel strength (N)
Concrete	29.1 N
Plywood	6.5 N

## 3. CYCLIC MOVEMENT

### 3.1 Testing

Testing carried out in accordance with AS4654.1 Appendix B Assessment of resistance of waterproofing membranes to cyclic movement.

### 3.2 Results

Note : Results from testing WPM 750 membrane

Number of cycles:	50
Cycle Time:	2 hours
Cycle expansion:	50% of control elongation at break
Sample size:	65 mm x 25 mm
Sample span:	4 mm between plates
Sample thickness:	0.85 mm

The test sample achieved a control elongation at break of >500% as per AS4654 Appendix A. For a Class III membrane the extension movement used for cycling is 4mm.

Number of cycles completed:	50
Surface crazing:	Nil



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**5 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

Surface tears: Nil

Membrane rupture: Nil

**Result:** Meets the requirement for the Moving Joint Test

## 4. DIMENSIONAL STABILITY

### 4.1 Testing

Test carried out in accordance with D6207-03.

### 4.2 Results

Orientation	Length measurements (mm)					Initial - Final readings (mm)	Max change in length (mm)
	Initial Dry reading	Cycle 1 readings		Cycle 2 readings			
		Wet	Dry	Wet	Dry		
Lengthwise	901	900	901	900	902	-1	2
Widthwise	900	898	901	898	900	0	3

## 5. ELONGATION AT BREAK

### 5.1 Testing

Test carried out in accordance with AS4654.1 Appendix A.

### 5.2 Results

Results are an average of 6 samples.

Note : Results from testing WPM 750 membrane

Mean sample thickness (mm)	Tensile strength (MPa)	Elongation at break (%)
0.85	>4.07	>500

**Requirement for Class III:** The specimens have an elongation at break of >300%

**Classification:** Class III (high extensibility)

## 6. HEAT AGEING

### 6.1 Testing

Testing carried out in accordance with AS4654.1 Appendix A.



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**6 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

## 6.2 Results

Note : Results from testing WPM 750 membrane

Results are an average of 6 samples.

Mean sample thickness (mm)	Tensile strength (MPa)	Elongation at break (%)
0.85	>4.11	>450

**Requirement:** The specimens require an elongation at break greater than 50% of the control sample. There was no deterioration in the elongation at break performance.

**Result :** Pass

## 7. TEMPERATURE RESISTANCE

### 7.1 Testing

Testing carried out in accordance with AS4654.1 Appendix A. Samples were exposed for 2 days at 85°C and samples were exposed for 2 days at -15°C.

### 7.2 Results

Results are an average of 6 samples.

Note : Results from testing WPM 750 membrane

#### High temperature, 85°C

Mean sample thickness (mm)	Tensile strength (MPa)	Elongation at break (%)
0.85	>3.99	>500

#### Low temperature, -15°C

Mean sample thickness (mm)	Tensile strength (MPa)	Elongation at break (%)
0.85	>4.16	>500

**Requirement:** The membrane shall remain waterproof when subjected to temperatures likely to be encountered in use: for Australia these would be within the range -15°C to 85°C.

Samples shall exhibit no cracking, fractures or surface defects after exposure.

**Result :** Pass



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**7 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.

## 8. TENSILE STRENGTH

### 8.1 Testing

Testing carried out in accordance with AS4654.1 Appendix A.

### 8.2 Results

Results are an average of 6 samples.

Note : Results from testing WPM 750 membrane

Mean sample thickness (mm)	Tensile strength (MPa)	Elongation at break (%)
0.85	>4.07	>500

## 9. DURABILITY

### 9.1 Testing

Testing carried out in accordance with AS4654.1 Appendix A.

### 9.2 Results

Note : Results from testing WPM 750 membrane

	Tensile Strength	Elongation at break	Pass / Fail
Control	>4.07 MPa	>500 % Elongation	N/A
Water immersion	>3.99 MPa	>500 % Elongation	Pass
Detergent immersion	>3.90 MPa	>500 % Elongation	Pass
Heat ageing	>4.11 MPa	>450 % Elongation	Pass
Bioresistance	Manufacturing guidelines for bioresistance to be followed		

## 10. WATER VAPOUR TRANSMISSION RATE

### 10.1 Testing

Testing carried out in accordance with ASTM E96 desiccant method.

### 10.2 Results

Note : Results from testing WPM 750 membrane



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**8 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.



Thickness (mm)	WVTR (g/m <sup>2</sup> /24 hours)	Minimum result (g/m <sup>2</sup> /24 hours)	Maximum result (g/m <sup>2</sup> /24 hours)
0.85	0.23	0.20	0.27



REPORT NUMBER:

**DC2893/7**

ISSUE DATE:

**21 August 2017**

PAGE:

**9 of 9**



THE LEGAL VALIDITY OF THIS REPORT CAN ONLY BE CLAIMED ON PRESENTATION OF THE COMPLETE SIGNED PAPER REPORT.  
EXTRACTS OR ABRIDGMENTS OF THIS REPORT SHALL NOT BE PUBLISHED WITHOUT PERMISSION FROM BRANZ LTD.