



ANALYSIS CERTIFICATE


20 March, 2024

OUR REF:	111105
TO:	Ardex NZ Ltd
ATTN:	Ines Jakob

SAMPLE OF:	Ardex AF-460	SAMPLE TYPE:	As received
SAMPLE TYPE:	Engineered Wood Adhesive	DATE RECEIVED:	20/03/2024
SAMPLE DATE:	-	DATE TESTED:	20/03/2024
		ORDER NO:	-

	Result	Method
Total Non-Volatile Content, %w/w	98.7	Oven-drying @ 110°C (60mins)
Total Water Content, %w/w	<0.1	Karl Fischer titration
Density, g/mL	1.82	Gravimetry
Exempt Compounds	None specified	

	Result	Method
Total Volatile Organic Compounds, g/L	24	SCAQMD METHOD 304-91



Analyst



Authorised by

This report relates only to the sample provided

This Report Shall Not Be Reproduced Except In Full
MEMBER OF THE NEW ZEALAND ASSOCIATION OF CONSULTING LABORATORIES